

Streichputz grob



Product description

Characteristics:

- Non-slip and high quality brush-on plaster on dispersion basis
- Rough structure
- Structuring grout with good hiding and filling power
- Even structure when applied by roller
- Structuring possible when applied by brush
- Suitable as primer for following plasters
- Ideal underground for following varnishing
- For exterior and interior use
- Gloss level: mat
- Free of solvents and harmful emissions
- With CE-labelling

* Test certificate available on request.

Material

| | |
|---------------------------|--|
| Application Area: | For exterior and interior use on new and old solid undergrounds, such as stucco, concrete and gypsum board (without lignin marks). As priming coat for following applications with dispersion paints and resin plasters. |
| Binding agent: | Special resin dispersion |
| Colour: | White |
| Content of solids: | Approx. 71 % |
| Specific gravity: | 1.50 g/cm ³ |
| pH value: | Approx. 10 |
| Diluting agent: | Water |
| Viscosity: | Slightly thixotropic |



JONAS Streichputz grob



Application characteristics


| | |
|------------------------------------|--|
| Application: | Brush / roller / spray (with special equipment). Do not apply on sun heated substrates, during strong winds, at high temperatures, extremely high humidity, in fog or rain. Consider the risk of night frost. If necessary, protect the façade with suitable scaffolding-nets or tarpaulins. |
| Underground: | Needs to be clean, dry, and solid. Otherwise use JONAS Hydro-Haft-& Tiefgrund first to consolidate the underground. For underground treatment and application VOB, part C, DIN 18363 and the relevant BFS information must be observed. |
| Coating build-up: | Dilute priming coat with 5% water. |
| Spreading rate per coating: | Approx. 400 – 500 g/m ² on smooth underground (if necessary test on the wall). |
| Application temperature: | At least + 5°C (Degrees Celsius) for air and underground during application and drying. |
| Drying: | <p>The surface of the coating is touch-dry after 24 hours. Final hardness after approx. 2 weeks (at a temperature of 20 °C and a relative atmospheric humidity of 65 %). High humidity, low temperatures and low air exchange extend the hardening and drying time.</p> <p>In case of adverse weather conditions always take appropriate actions (e.g. rain protection) to protect work areas and freshly painted surfaces.</p> |
| Tinting: | <p>Product can be tinted with JONAS Allcolor Vollton- und Abtönfarben. Tinting may lead to deviations in the technical data, also with respect to contents of preservatives.</p> <p>Colour stability: weather, humidity, UV-light and accumulations may have an influence on the coating surface. The process of change is dynamic and depends on climate and exposition conditions. The current national regulations, leaflets etc. apply.</p> <p>Colour accuracy: weather conditions and property conditions have an influence on colour accuracy and the uniformity of colour. The following conditions should be avoided:</p> <ol style="list-style-type: none">Irregularly sucking substrateDifferent surface humidity in the substratePatches with different alkalinity and / or ingredients from the substrateDirect sunlight with sharp shadows on the still humid coating <p>Washout of additives: For coatings which are not yet fully dried any water impact, i.e. dew, fog or rain, may washout additives from the coating which then build-up on the surface. The extent of this effect differs, depending on the intensity of the colour. This has no influence on the quality of the product. The effect will disappear under normal weather conditions.</p> |
| Cleaning of tools: | Clean with water immediately after use. |

JONAS Streichputz grob



General information

| | |
|---------------------------------------|---|
| Storage: | Cool, but not freezing. |
| Shelf-life: | Can be stored for at least 12 months after date of filling (see additional sticker) if stored properly in the unopened original packaging. |
| Art.No. and description: | 31 05 001 JONAS Streichputz grob |
| Packaging: | 20 kg / 8kg |
| Ingredients acc. to. VdL RL01: | Resin dispersion, white pigment, calcium carbonate, water, additives, preservatives, BIT/MIT. |
| Safety: | Please follow the instructions of the safety data sheet. |
| Labelling: | This product is not classified according to EU regulation No 1272/2008 [CLP]. |
| Product-Code: | BSW20 |
| VOC content: | EU limit for the product Kat. A/a: 30 g/l (2010). This product contains < 1 g/l VOC. |
| Waste disposal: | Empty containers can be disposed for recycling. Any dried residues of material can be disposed of as construction waste or together with domestic garbage. Containers with liquid material residues must be disposed of according to local regulations. For further information, please contact your local waste authority. |
| CE-labelling: | According to EN 15824 for stucco with organic binder for interior use. Declaration of performance no. 01-5 |

| | | |
|--|---|---|
|  JONAS Farben GmbH Dieselstraße 42-44 42489 Wülfrath 11 | Brandverhalten: | Klasse B-s1, d0 (bei Verwendung auf mineralischen Untergründen) |
| | Wasseraufnahme: | keine Leistung festgestellt |
| | Wasserdampfdurchlässigkeit μ : | keine Leistung festgestellt |
| | Haftfestigkeit: | $\geq 0,3$ MPa |
| | Dauerhaftigkeit (Frostwiderstand): | keine Leistung festgestellt |
| | Wärmeleitfähigkeit λ_{10} , dry, mat: | keine Leistung festgestellt |
| EN 15824 Putz mit organischen Bindemitteln zur Verwendung im Innenbereich | | |

*Flammability class B-s1, d0 (for use on mineral substrates.)

(The classification only applies if in practical use the construction product is used on base boards made of gypsum or base boards classified A1 or A2-s1, d0 according to DIN EN 13501-1 and with a gross density of 525 kg / m³).

Water absorption: no performance determined.

Water vapour permeability μ : no performance determined.

*** Adhesive strength:** $\geq 0,3$ MPa

Durability (frost resistance): no performance determined.

Thermal conductivity λ_{10} , dry, mat: no performance determined.

Advice for use and safety acc. to CLP:

Keep out of reach of children. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Wear appropriate respiratory protection (full mask / half mask equipped with filter type A2/P2). Avoid eating, drinking and smoking during use of the product. Ensure good ventilation during and after application. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not empty into drains or water courses. Contains: 1,2-Benzisothiazol-3(2H)-on / 2-Methyl-2H-isothiazol-3-on. Safety data sheet available on request. Advice for people suffering from isothiazolinone allergy under phone-no.: +49(0)2058/789-0.