

## Technical data sheet

# Renoplast



### Product description

**Characteristics:**

- Silk-glossy plastic for interior use with good modelling characteristics
- For renovation of e.g. stairways, hallways, schools, kinder gardens, hospitals.
- Very durable
- Fast and homogeneous spreading
- High degree of whiteness
- Fine structure
- Silk gloss
- Preservative-free
- Free of solvents and harmful emissions

**DIN EN 13300:**

- Wet scrub resistance: R-class 2
- Contrast ratio: hiding power H<sub>10</sub>-class 1 (≥ 99.5) at a spreading rate of 220 g/m<sup>2</sup>
- Gloss level: G2b medium gloss
- Maximum particle (grit) size: fine (< 100 µm)

### Material

<b>Application Area:</b>	For interior use on good, solid new and old undergrounds such as stucco, concrete, gypsum board (without lignin marks).
<b>Binding Agent:</b>	Special resin dispersion
<b>Colour:</b>	White
<b>Content of Solids:</b>	Approx. 57 %
<b>Specific gravity:</b>	1.39 g/cm <sup>3</sup>
<b>pH value:</b>	Approx. 10
<b>Diluting agent:</b>	Water
<b>Viscosity:</b>	Slightly thixotropic

### Application Characteristics

<b>Application:</b>	Brush / roller / shape as needed with appropriate tools
<b>Underground:</b>	Needs to be clean, dry, and solid. Otherwise use JONAS Hydro-Haft- & Tiefgrund first to consolidate the underground. For underground treatment and application VOB, part C, DIN 18363 and the relevant BFS information must be observed.
<b>Coating build-up:</b>	Priming coat: No dilution or dilute product with a maximum of 5% water. Final coating: use product without dilution.
<b>Spreading rate per coating:</b>	Approx. 0.5 – 1.0 kg/m <sup>2</sup> based on structure and application thickness (if necessary test on the wall).
<b>Application temperature:</b>	At least + 5°C (Degrees Celsius) for air and underground during application and drying.
<b>Drying:</b>	The surface of the coating is dry and can be painted over after 8 - 10 hours (at a temperature of 20 °C and a relative atmospheric humidity of 65 %). High humidity, low temperatures and low air exchange extend the hardening and drying time.

# Technical data sheet

# JONAS Renoplast



## Application Characteristics

<b>Tinting:</b>	Product can be tinted with JONAS Allcolor Vollton- und Abtönfarben up to 10%. Higher mixtures decrease the glare. Tinting may lead to deviations in the technical data, also with respect to contents of preservatives.  Colour accuracy: property conditions have an influence on colour accuracy and the uniformity of colour. The following conditions should be avoided: <ul style="list-style-type: none"><li>a. Irregularly sucking substrate</li><li>b. Different surface humidity in the substrate</li><li>c. Patches with different alkalinity and / or ingredients from the substrate</li></ul>
<b>Cleaning of tools:</b>	Clean with water immediately after use.

## General information

<b>Storage:</b>	Cool, but not freezing.
<b>Shelf-life:</b>	Can be stored for at least 12 months after date of filling (see additional sticker) if stored properly in the unopened original packaging.
<b>Art.No. and description:</b>	09 50 001 JONAS Renoplast
<b>Packaging:</b>	20 kg
<b>Ingredients:</b>	Resin dispersion, white pigment, calcium carbonate, silicate, water, additives.
<b>Preservative-free:</b>	Preservative-free according to VdL guideline 01 or equivalent RAL DE-UZ102.
<b>Safety:</b>	Please follow the instructions of the safety data sheet.
<b>Labelling:</b>	This product is not classified according to EU regulation No 1272/2008 [CLP].
<b>GISCODE:</b>	BSW10
<b>VOC content:</b>	EU-Limit for the product Kat. A/b: 100 g/l (2010). This product contains < 1 g/l VOC.
<b>Waste disposal:</b>	Empty containers can be disposed for recycling. Any dried residues of material can be disposed of as construction waste or together with domestic garbage. Containers with liquid material residues must be disposed of according to local regulations. For further information, please contact your local waste authority.
<b>Advice acc. to CLP:</b>	Keep out of reach of children. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Wear appropriate respiratory protection (full mask / half mask equipped with filter type A2/P2). Avoid eating, drinking and smoking during use of the product. Ensure good ventilation during and after application. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not empty into drains or water courses. Safety data sheet available on request.